



➤ Exact Air

Stone wool slab for professional vegetable growing



Product description

Cultilene Exact Air is a stone wool slab, mainly made of basalt and with Gradient technology. The density of the stone wool increases progressively from the bottom of the slab to the top. This results in minimal differences in water content, EC, pH and oxygen levels. Exact Air is also characterised by having fewer water roots and by having a good root distribution throughout the entire slab.

Product application

Cultilene Exact Air slabs are used for growing vegetable crops under glass or plastic.

Guarantee

The guaranteed lifespan of the stone wool substrate and foil is one crop if used under normal growing conditions in high tech greenhouses.

Exact Air is produced under RHP certification. The RHP certificate is a quality agreement between the stone wool suppliers and the Dutch trade association for the plant reproduction material sector.

The KIWA certification agency regulates this certification scheme. Further information can be found at the RHP website: www.rhp.nl

Why choose Cultilene Exact Air?

- ✓ Less water roots and more air roots
- ✓ Wider range of dose sizes
- ✓ Good control in all conditions



Product characteristics

The Exact Air slab is just one of the solutions from Cultilene for growing plants. This controllable water buffer has the following characteristics:

Parameter	
Time required to sink	Class 1 RHP < 25 sec
Nominal water content - at drainage	90%
Nominal water content - pF1	65%
Control range *	50 – 80%

* Indication of average values in practice.
The RHP standard applies to the minimum values.

Technical details

Physical requirements

Parameter	
Organic matter	1,0 – 5,5%
Bulk density at delivery	52 kg/m³ *
Relative compression (RC)	≤ 30% bij 5 kPa
Recovery capacity	≥ 98% +/- 2% bij 5 kPa
Pore volume	≥ 95%

* Tolerance + / - 10%.

Chemical requirements

Parameter	Normen
EC	≤ 0,5 dS/m
pH value in stone wool	5 – 6,5

Substrate tolerances

The following tolerances apply to the nominal dimensions of the final product (dry product):

Dimensions of slabs	
Length	+ / - 7 mm
Width	+ / - 5 mm
Height	+ / - 5 mm

Plant holes in slabs	
Centre-to-centre spacing	+ / - 2 mm
Position of first hole	+ / - 10 mm
Centre hole to slab edge (side)	+ / - 10 mm
Depth of hole	+ / - 3 mm
Diameter of hole (round holes)	+ / - 2 mm
Length x width (other holes)	+ / - 2 mm

Standard product dimensions


The most commonly used dimensions for Exact Air slabs are a combination of the following length, width and height measurements:

Length (mm)			
	150	200	240
500	x	100	100
1000	75 100	75 100	x
1200	75 100	75	x
1330	75 100	75 100	x
2000	75 100	75 100	x

Alternative sizes are available on request.

If desired, the Exact Air slabs are provided with plant holes. After production and processing, the slabs are stacked on pallets and prepared for transport.

Control range






Exact Air





For effective water management and optimal root distribution

Packaging and storage

Exact Air slabs are delivered in standard packaging on standard pallets (1200 x 1000 mm). Different pallet sizes are available on request.

Each pallet has a pallet label with information such as the production order number, item number, product description and product characteristics.

 SAINT-GOBAIN																																
1851439-EA1649-PHS-001																																
Itemcode EA1649-PHS	Dimensions (LxWxH) 1330 X 200 X 85	Contents 90 STUKS																														
Deliv.very Address:		Exact® Air ingehuld plantg.folie																														
		Exact® Air wrapped pl.holes foil																														
<table><tr><td>Productomschrijving:</td><td>Substraat van wateropneembare minerale vezel</td></tr><tr><td>Samenstelling:</td><td>Hoofbestanddeel: Minerale steen of korreling</td></tr><tr><td>Eigenschappen:</td><td>Buikdichtheid voor aflevering: 52 kg/m³</td></tr><tr><td></td><td>Porositeit: 95%</td></tr><tr><td></td><td>Watergehalte bij aflevering: 95%</td></tr><tr><td></td><td>Watergehalte bij gebruik: 3-4 vol. %</td></tr><tr><td>Volgvoorschriften:</td><td>Aanwijzing onder gebruik: uitsluitend gebruik dient te worden voorkomen. De rest de "Gedrukte instructies"</td></tr><tr><td>Productie:</td><td>Substraat van wateropneembare minerale vezel</td></tr><tr><td>Compositie:</td><td>Minerale steen / Minerale steen / Minerale steen</td></tr><tr><td>Properties:</td><td>Buikdichtheid voor aflevering: 52 kg/m³</td></tr><tr><td></td><td>Porositeit: 95%</td></tr><tr><td></td><td>Watergehalte bij aflevering: 95%</td></tr><tr><td></td><td>Watergehalte bij gebruik: 3-4 vol. %</td></tr><tr><td>Safety instruct:</td><td>Teach without danger, inner use should be prevented</td></tr><tr><td></td><td>See also: "Practical instructions for use"</td></tr></table>			Productomschrijving:	Substraat van wateropneembare minerale vezel	Samenstelling:	Hoofbestanddeel: Minerale steen of korreling	Eigenschappen:	Buikdichtheid voor aflevering: 52 kg/m³		Porositeit: 95%		Watergehalte bij aflevering: 95%		Watergehalte bij gebruik: 3-4 vol. %	Volgvoorschriften:	Aanwijzing onder gebruik: uitsluitend gebruik dient te worden voorkomen. De rest de "Gedrukte instructies"	Productie:	Substraat van wateropneembare minerale vezel	Compositie:	Minerale steen / Minerale steen / Minerale steen	Properties:	Buikdichtheid voor aflevering: 52 kg/m³		Porositeit: 95%		Watergehalte bij aflevering: 95%		Watergehalte bij gebruik: 3-4 vol. %	Safety instruct:	Teach without danger, inner use should be prevented		See also: "Practical instructions for use"
Productomschrijving:	Substraat van wateropneembare minerale vezel																															
Samenstelling:	Hoofbestanddeel: Minerale steen of korreling																															
Eigenschappen:	Buikdichtheid voor aflevering: 52 kg/m³																															
	Porositeit: 95%																															
	Watergehalte bij aflevering: 95%																															
	Watergehalte bij gebruik: 3-4 vol. %																															
Volgvoorschriften:	Aanwijzing onder gebruik: uitsluitend gebruik dient te worden voorkomen. De rest de "Gedrukte instructies"																															
Productie:	Substraat van wateropneembare minerale vezel																															
Compositie:	Minerale steen / Minerale steen / Minerale steen																															
Properties:	Buikdichtheid voor aflevering: 52 kg/m³																															
	Porositeit: 95%																															
	Watergehalte bij aflevering: 95%																															
	Watergehalte bij gebruik: 3-4 vol. %																															
Safety instruct:	Teach without danger, inner use should be prevented																															
	See also: "Practical instructions for use"																															
NR 3759 MADE IN CZECH REPUBLIC																																
Leveringsduur / longevity: 1 jaar / Annual																																

-  Production order number
(last three numbers are the pallet number)
-  Article number / size of the slab / slabs per pallet
-  Description of the slab
-  Product characteristics

The pallets must be stored (indoors) in their original packaging in a dry place and away from direct sunlight. The products must be used within two years of the delivery date. Pallets must be stacked no more than 2 high, and we would like to emphasise that the safety rules that apply to stacking pallets must be observed. Ensure the prevention of damage to the packaging material.

User instructions

Exact Air slabs must be completely saturated with water before use. Leave the slabs for a minimum of 24 hours (preferably 48 hours) fully saturated with water at the EC and pH prescribed for your crop.

Then make the drainage slits within 24 hours before

planting. The position of the drainage slits in combination with the correct dose size will influence the distribution of water and EC in the slab and the drainage of elements. It is important to minimize the fluctuations in water content and EC throughout the whole slab because these fluctuations will have a major impact on the root distribution in the slab.


Making drainage slits is a measure that must be done with care because it will influence the growth of the plant for the rest of the season.

The objective is to get a homogeneous water content and EC throughout the slab. If extra drainage slits are made later during cultivation, the distribution of water and EC in the slab will change and this will have impact on the quality of the roots. Additional tips for making drainage slits:

- make drainage slits at the lowest point on both ends of the slab. The drainage slits located between the ends must be made exactly between the cubes;
- this results in an even drainage pattern throughout the slab so that water and fertilizers can be refreshed more effectively and more efficiently;
- if the slab is not absolutely level when using hanging gutters, drainage slits can be made on both sides to ensure the drainage is the same throughout the slab.
- all drainage slits must run to the bottom of the slab and have to be high enough (3 – 4 cm). In order to prevent the roots from restricting the flow of drainage water;
- never make a drainage slit under a dripper as this can lead to 'false drainage'.

The target level for moisture content is between 50% and 80% of the volume.

▲ = Drainage slit ↓ = Dripper



Environmental, health and safety concerns

Environmental concerns: recycling

Cultilene devotes a great deal of attention to the recycling of raw materials, both at our own production locations and, after use, at growers' locations. The recycled stone wool can be used, for example, in the production of bricks.

For more information about the recycling of your stone wool, you can contact your Cultilene representative.

Health concerns

If you are in direct contact with stone wool substrate, we advise you to wear gloves. In insufficiently ventilated spaces, we advise the use of a face mask. Wash your hands before and after handling the stone wool substrate. You can best do this by first rinsing your hands with water to get rid of the dust. Then wash your hands with soap.

In case of irritation to eyes or mouth; rinse with clean water and consult a doctor if necessary.

Stone wool from Cultilene is a 'mineral wool' produced in certified EUCEB factories. EUCEB certifies the conformity of stone wool fibres with Note Q of Regulation (EC) No. 1272/2008.

Safety concerns

If needed, we can supply you with the General Safety Information Sheet for Stone Wool (Safe Use Information Sheet - SUIIS).

Certification

All Cultilene production and manufacturing sites in Europe are certified with the ISO 9001 & 14001 standards.

In addition, Exact Air is included in the RHP certification MOD550 stone wool substrate.

Knowledge

Please refer to the Cultilene Framework for more information about the propagation and growing phases. This can be found at app.cultilene.com.



Scan the QR-code
for how-to videos
and white papers



Would you like more information about the **Exact Air slab**?
Get in touch!

► **Saint-Gobain Cultilene B.V.**
+31 (0)161 22 87 40
info.cultilene@saint-gobain.com
www.cultilene.com